

SHREE EXTRUSIONS LIMITED



C66800 Processing and Property: Excellent hot and cold workability; good forge ability. Fabricated by bending, coining, coppersmith, drawing and upsetting, hot forging and pressing, knurling, roll threading, shearing, spinning, swaging, and stamping.

TYPICAL USES:

INDUSTRIAL: Gears, Sealing Rings, Thrust Bearings, Bushings, Cams, Spindles, Bearings, Idler Pins, Connecting Rods, Drive Shafts, Valve Seats, Sleeve Bearings, Piston Heads **MARINE:** Pump Parts, Hardware, High Strength

CHEMICAL COMPOSITION

	Cu	Al	Fe	Pb	Mn	Ni	Si	Sn	Zn
Min./Max.	60.0-63.0	.25	.35	.50	2.0-3.5	.25	.50-1.5	.30	Rem.
Nominal	61.5	-	-	-	2.7	-	1.0	-	-

PHYSICAL PROPERTIES

Young's Modulus	16700 ksi
Density	0.300 lb/in3
Melting Range	1690 - 1730 oF
Coefficient of Expansion	(68 to 572oF) 11 +in/in oF
Thermal Conductivity	55 Btu/ft h oF
Electrical Conductivity	21 % IACS
Electrical Resistivity	$54~\Omega$ (circ mil/ft)
Relative Magnetic Permeability	<1.02
Coefficient of Friction	0.15

SIZES AVAILABLE:

ROUND RODS

8mm To 100 mm

10mm To 100mm

SQUARE

10mm To 60mm

10mm Min Thickness and max Width 120mm

BILLETS

Up to 200 mm

INGOTS

As per Specification

Regd. Office & Works:

217/218 Phase-II, Okha Rajkot Road, Dared, Jamnagar - 361 004. INDIA Tel.: +91 - 288 - 2730118 I Mobile: +91 - 9328105172 mail@shree-extrusion.com I www.shree-extrusion.com



