

SHREE EXTRUSIONS LIMITED



C95800 offers superior salt water corrosion resistance. It also is resistant to cavitation and erosion. Along with the advantage of pressure tightness, this high strength alloy is excellent for welding and is available in many forms at a lower cost to you.

Cast ASTM: B271, B505, B148 Military/AMS: MIL-B-24480 Other: ABS - 4

COMMON APPLICATIONS:

Piping for Vertical Pump Columns, Firefighting and Fire Suppression Systems, Seawater Lift Pumps, Piping Layout, Flanges and Fittings, Discharge Elbows, Cooling Loops for Power Plants

Bronze Valve Bodies, Piping Systems, Desalination Equipment, Tube Sheets, Circulating Pumps and Pump Shafts, Fasteners, Hardware for Cooling towers

CHEMICAL COMPOSITION

	Al	Cu	Fe	Pb	Mn	Ni	Si
Min/Max	8.5-9.5	79.0 min	3.5-4.5	0.03	.8-1.5	4.0-5.0	0.1
Nominals	9.0000	81.0000	4.0000	-	1.0000	4.5000	-

PHYSICAL PROPERTIES

Product Property	US Customary				
Coefficient of Thermal Expansion	9.0 •10-6 per oF (68-572 F)				
Density	0.276 lb/in3 at 68 F				
Electrical Conductivity	7 %IACS @ 68 F				
Electrical Resistivity	146.7 ohms-cmil/ft @ 68 F				
Information not available on website					
Magnetic Permeability	1.05				
Melting Point - Liquidus	1940 F				
Melting Point - Solidus	1910 F				
Modulas of Elasticity in Tension	16500 ksi				
Poisson's Ratio	0.32				
Specific Gravity	7.64				
Specific Heat Capacity	0.105 Btu/lb/oF at 68 F				
Thermal Conductivity	20.8 Btu • ft/(hr • ft2 • oF)at 68F				

SIZES AVAILABLE:

ROUND RODS

8mm To 100 mm

10mm To 60mm

SQUARE

10mm To 60mm

10mm To 60mm

10mm Min Thickness and max Width 120mm

BILLETS

Up to 200 mm

INGOTS

As per Specification

Regd. Office & Works:

217/218 Phase-II, Okha Rajkot Road, Dared, Jamnagar - 361 004. INDIA

Tel.: +91 - 288 - 2730118 | Mobile: +91 - 9328105172 mail@shree-extrusion.com | www.shree-extrusion.com



